# **Technical Data Sheet**

Bondloc BCA MV Superglue Revised 03.08.10



# **Bondloc BCA MV Superglue**

## **APPLICATIONS**

BCA MV Superglue bonds metals, plastics, wood, ceramics, rubber, leather, card, glass and many other materials

#### INSTRUCTIONS FOR USE

Clean and dry surfaces to be bonded. Apply adhesive sparingly to one surface and assemble parts. Hold or clamp parts together for 60 seconds. Leave for 1 hour to fully cure. Activators and primers may be used to aid bonding.

## LIQUID PROPERTIES

Ester base	Ethyl cyanoacrylate
Appearance	Clear, colourless
Specific Gravity 25°C	1.06 g/cm2
Shelf life	12 months unopened
Viscosity @ 25°C	90 – 120cps
Flash Point	85°C

### **CURED PERFORMANCE**

Cured speed – defined as the time taken to develop a strength of 0.1N/mm² at 22°C and 50% relative humidity.

Balsa	<3 seconds
Nitrile	<5seconds
Neoprene	<5 seconds
EPDM	<5 seconds
Steel	25-40 seconds
Polycarbonate	10-30 seconds
ABS	10-15 seconds

#### SHEAR STRENGTH

Steel	25 N/mm²
Aluminium	7-10 N/mm²
Nitrile Rubber	5-10 N/mm²
Polycarbonate	5-10 N/mm²
ABS	6-10 N/mm²

### **TENSILE STRENGTH**


Nitrile Rubber	5-15 N/mm²
Neoprene	5-15 N/mm²
EPDM	2-6 N/mm²

#### **TEMPERATURE RESISTANCE**

Tested on mild steel cured for 24 hours, conditioned to test temperature for 1 hour before pull-test.

#### **ENVIRO-CHEMICAL RESISTANCE**

Exposed to conditions for 1000 hours at 22°C except for 98% RH which had an exposure of 42°C.



#### **STORAGE**

BCA MV should ideally be stored in original sealed containers until used. Containers should be stored between 2°C and 10°C with a maximum storage temperature of 25°C. Avoid exposure to strong light and heat sources. Refrigeration can prolong shelf life.

#### **HEALTH & SAFETY**

This technical information sheet does not constitute a Material Safety Data Sheet (MSDS). Before using this product ensure you have read and fully understood BCA MV MSDS.

#### **PRESENTATION**

Bottles......10g, 20g, 50g, 500g